

SuperMax Oil Germany Green Grease

Multi Purpose Rubber Grease



PRODUCT DESCRIPTION

SuperMax Oil Germany Green Grease is a dark green grease, prepared to blending with well-refined mineral based oils and calcium soap additives. It can be used in applications at the low and medium operating temperature. It's advised lubricating hydraulic turbines and roller bearing bed up to 70°C and automotive applications up to 65°C.

ADVANTAGES

- High resistance of corrosion and abrasion.
- Provide to excellent protection according to fibrous tissue.
- Lower consumption for adhere metal surfaces and provided to economical usage.
- High water resistance.

CHARACTERISTIC PROPERTIES

| Analysis | Unit | Ideal Values | | |
|-------------------------------|------|--------------|-----------|-----------|
| | | 1 | 2 | 3 |
| NLGI | - | 1 | 2 | 3 |
| Soap Type | - | Calcium | Calcium | Calcium |
| Worked Penetration, 25°C | - | 310-340 | 265-295 | 220–250 |
| Dropping Point | °C | 95 | 95 | 95 |
| Maximum Operating Temperature | °C | 60 | 60 | 60 |
| Water Resistance | - | Excellent | Excellent | Excellent |
| Low Temperature Mobility | - | Fair | Fair | Fair |

STORAGE

Packages should be stored in cool, well-ventilated and covered areas; and their taps should be tightly closed and sealed when not in use. Packages should not be exposed to direct sunlight and avoid rapid climatic changes. Ambient temperature should not exceed 50 °C.

SuperMax Oil Germany Green Grease

Multi Purpose Rubber Grease



SHELF LIFE

Under the appropriate storing conditions suitable to the declared circumstances, maximum shelf life of the products are two years.

HEALTH AND SAFETY

Based on the available information, SuperMax Oil Germany Green Greases are not expected to produce adverse effects on health when used for the intended application and aligned with the recommendations provided in the; "Material Safety Data Sheet" (MSDS). MSDS's are available upon request through your sales contact office or representative.

When disposing the used product, physical and chemical properties has to be taken into the consideration, and please follow the regional or national regulations